

Panel | Acoustic

Felt 9900





Felt 9900

Panel | Acoustic

Specifications

Content	80% polyester 20% post-consumer recycled polyester
Weight	10.2 ± 1.0 oz./lin. yd
Width	64" min. useable
Repeat	none

Performance

 Colorfastness to light (AATCC 16.3 Option 3)	Grade 4 min. at 40 hours
 Colorfastness to crocking (AATCC 8)	Grade 4 min. dry & Grade 3 min. wet
 Breaking Strength (ASTM D5034)	250 lbf min. warp and 125 lbf min. fill
 Flammability	ASTM E84 Class I or A

Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

Acoustical Performance

Our acoustic fabrics are all acoustically transparent. This represents the amount of sound that passes through the fabric.


Acoustic Transparency: 99%

For more detailed results, please consult our website.

Miscellaneous

- Application testing of this product is recommended.
- Colors may vary between dye lots.
- This is a non-directional fabric.

*Light fabric are subject to transparency issues depending on lighting intensity and internal structure. Application testing of this product is recommended.

 This pattern is included in the underwriters laboratory panel fabric recognition program. Additional testing of this U.L. recognized fabric is not required on approved panels from participating manufacturers.

Certification Marks owned by the Association for Contract Textiles, Inc.

This product is a Feltväri™ non-woven.

Proudly made in North America supporting our local communities.



White* 8888		Maize 3204	
	Dune 3062	Pear 3210	Cherry 3362
Ivory 3206	Aluminum 3055	Liberty 3053	Deep Sea 3054
Pebble 3056	Sterling 3057	Ebony 3059	

duvaltex

USA & INTERNATIONAL | T 800-544-0200
CANADA | T 418 227-9897
For samples, visit duvaltex.com